

Kind of production Steels in Machine Sazi Arak

GROUP	AISI/ASTM	DIN/EN		UNS	ROSCHLING
		MATERIAL	NAME		
Carbon Steel	A 105	1.0432	C21	K03502	--
	A 350-LF2	1.0508	--	K03011	--
	A350-LF6	1.8912	--	K12202	--
	A266 Gr. 2	---	--	K03506	--
	A266 Gr.4	--	--	K03017	--
	A694-F42...F70	--	--	--	--
	A284 -D	1.0114	St37	K01501	--
	A366-F1	---	--	K12520	--
	1035	1.1181	CK35	G10350	R3
	1038			G10380	
	1045	1.1191	CK45	G10450	RM4
	1055	1.1203	CK55	G10550	--
	--	1.0565	P 355 NH	K0565	
	--	1.0570	St52-3	K11430	--
	Alloy Steel	5115	1.7131	16MnCr5	G51150
--		1.6582	34CrNiMo6	G43370	MoNiX15
4140		1.7225	42CrMo4	G41400	Mo40
4130		1.7218	25CrMo4	G41300	Mo25
4135		1.7220	34CrMo4	G41350	
5140		1.7035	41Cr4	G51400	VC135
4340		1.6562	40NiCrMo8-4	G43400	--
A182-F11		1.7035	13CrMo 4-5	K11562	--
A592-F		1.8907	StE 500	--	--
L6		1.2713	55NiCrMoV6	T61206	RGS1
--		1.2312	40CrMnMoS 8 6	--	MFRS
H13		1.2344	X40CrMoV5	T20813	PDC2V
Stainless Steel	410	1.4006	X10Cr13	S41000	--
	420	1.4021	X20Cr13	S42000	RNO
	A182-F304	1.4301	X5CrNi 18-10	S30400	AKV7
	A182-F304L	1.4306	X2CrNi19-11	S30403	--
	A182-F316L	1.4404	X2CrNiMo17 13 2	S30500	--
	A182-F316	1.4401	X5CrNiMo17-12-2	S31600	ANOXIN4P
	A182-F321			S32100	
	--	1.4317	G-X4CrNi13 4	--	--
	--	1.4413	X 3 CrNiMo 13 4	S42400	--

